


# **EP-M450H**

Large Size & High Speed & Reliable Production Metal Additive Manufacturing System





### **EP-M450H**


With a building chamber size of 456\*456\*1080 mm³. EPlus 3D Introduces EP-M450H to the successful line of MPBF<sup>™</sup> 3D printers. The new EP-M450 is a marvelous metal printer that makes the production of reliable and high quality large metallic parts viable on industrial scale without requiring any tools.



Multi-oil pipeline assembly parts IN718 high temperature alloy 420\*420\*110 mm<sup>3</sup>



Engine turbine casing assembly IN718 high temperature alloy  $\phi~410^*240\text{mm}^3$ 



Engine leaf ring structure 316L stainless steel \$\phi400\*60mm^3\$



TC4 titanium alloy \$\phi\$ 393\*340mm<sup>3</sup>



#### **G** HIGH QUALITY

- · Printed parts' density > 99.9 %, deviation in parts' mechanical properties < 5 %.
- · The optimized gas flow design ensures efficient removal of smoke and splashes as well as achievement of uniform and consistent full size printing.
- · Dynamic software with ability to divide the model into different sections like upper and lower surfaces, core areas and small areas etc. Different process parameters can be applied individually to these parts for high printed part quality.
- · Repeatable positional accuracy along Z-axis of building direction ≤ ± 5 µ m.
- Overlapping deviation with dual laser printing  $\leq \pm 0.1$  mm. Overall mechanical properties of the printed part remains same when compared to printing results with the single laser machine.



#### HIGH EFFICIENCY

- Build chamber size (X\*Y\*Z): 456\*456\*1080 mm³, build chamber volume > 200 L.
- · Printing with increased layer thickness can be realized, increasing the production capacity.
- · With in-house developed processing software (EP-Hatch), optimized scanning strategies can be achieved yielding reduced print duration.
- · Optional dual laser system with 2\*500 W fiber lasers increases printing efficiency by 70 %.
- · Maximum building rate of 55 cm³/h.
- · Bi-directional powder re-coating method leads to reduced re-coating time.



#### RELIABLE

- · Excellent core optic components from world-class supplier and mature process control parameter algorithm provides highest part quality.
- · High quality uniform part printing due to excellent control over building environment and components.
- Tightly sealed build chamber maintains oxygen concentration <100 ppm and a stable pressure during printing.
- · Sustained monitoring of powder left in feeder and ability to add powder without stopping the machine ensures uninterrupted part printing.
- Double protection of chamber door is attained due to dual gas releasing ports on top of printing chamber.



#### COST-EFFECTIVE & EASY OPERATION

- · Blow back enabled coarse and fine filtration system ensures prolonged lifetime of filter over 1000 hrs.
- · Highly user friendly software interface and one-click printing technology makes printing super simplified.
- · Comparability with different types of recoater blades such as ceramic, PU, alloy steel etc.
- · Reduced gas consumption during printing <6 L/min helps reducing operation cost.
- · Traceable print records after every print and real-time display of readings for various sensors.



#### **OPEN SYSTEM**

- · Open parameters for editing laser power, scan speed, scan direction, up and down facing surfaces etc.
- · Open system ensures freedom to choose among wide range of metal powders available in market.
- · Process software can be integrated with Siemens NX software to realize effective planning of design, simulation and printing path planning, within one software and highly improving the production efficiency.
- $\cdot$  Process software supports SLC and CLI formats.



## EP-M450H PARAMETER

| Machine Model                  | EP-M450H   |
|--------------------------------|--|
| Build Chamber (XxYxZ)          | 456*456*1080 mm³   |
| Optical System                 | Fiber Laser 500W/1000W (single or dual-laser optional)   |
| Spot Size                      | 90-130 µ m   |
| Max Scan Speed                 | 8m/s   |
| Layer Thickness                | 20–120 µ m   |
| Building Speed                 | Single Laser : 15~35cm³/h<br>Dual Laser : 35~65cm³/h   |
| Material                       | Titanium Alloy, Aluminium Alloy, Nickel Alloy, Maraging Steel,<br>Stainless Steel, Cobalt Chrome, Copper Alloy, etc. |
| Power Supply                   | 380V, 50 / 60Hz, 25kW, 60A ( Dual Laser : 27kW, 65A )  |
| Gas Supply                     | $Ar/N_2$   |
| Forming chamber oxygen content | <100ppm  |
| Dimension (WxDxH)              | 8250*3850*4750mm³  |
| Weight                         | 15000kg  |
| Software                       | EPLUS 3D, EPHatch  |
| Input Data Format              | STL file or other convertible format   |

Notice: Eplus 3D reserves the right to explain anyalteration of the speciications and pictures.